

## Silicone Sealants

# Dow Corning® 795 Silicone Building Sealant

### FEATURES

- Suitable for most new construction and remedial sealing applications
- Versatile – high performance structural glazing and weathersealing from a single product
- Available in 11 standard colors; custom colors also available

### BENEFITS

- Excellent weatherability – virtually unaffected by sunlight, rain, snow, ozone and temperature extremes of -40°F (-40°C) to 300°F (149°C)
- Excellent unprimed adhesion to a wide variety of construction materials and building components, including anodized, alodined, most coated and many *Kynar*®1-painted aluminums<sup>2</sup>
- Ease of application – ready to use as supplied
- Ease of use – all-temperature gunnability, easy tooling and low-odor cure byproduct
- Meets global standards (Americas, Asia and Europe)

### COMPOSITION

- One-part, neutral-cure, RTV silicone sealant

### Neutral, one-part silicone sealant

### APPLICATIONS

- Structural and nonstructural glazing
- Structural attachment of many panel systems
- Panel stiffener applications
- Weathersealing of most common construction materials including glass, aluminum, steel, painted metal, EIFS, granite and other stone, concrete, brick and plastics

### TYPICAL PROPERTIES

Specification Writers: Please contact your local Dow Corning Sales Application Engineer or Dow Corning Customer Service before writing specifications on this product.

Method	Test	Unit	Result	
<b>As Supplied</b>				
ASTM C 679	Tack-Free Time, 50% RH	hours	3	
	Curing Time at 25°C (77°F) and 50% RH	days	7-14	
	Full Adhesion	days	14-21	
ASTM C 639	Flow, Sag or Slump	inches (mm)	0.1 (2.54)	
	Working Time	minutes	20-30	
	VOC Content <sup>1</sup>	g/L	28	
<b>As Cured – After 21 days at 25°C (77°F) and 50% RH</b>				
ASTM D 2240	Durometer Hardness, Shore A	points	35	
ASTM C 794	Peel Strength	lb/in (kg/cm)	32 (5.7)	
ASTM C 1135	Tensile Adhesion Strength	at 25% extension	psi (MPa)	45 (0.310)
		at 50% extension	psi (MPa)	60 (0.414)
		Joint Movement Capability	percent	±50
ASTM C 719	Staining (granite, marble, lime-stone, brick and concrete)		None	
<b>As Cured – After 21 days at 25°C (77°F) and 50% RH followed by 10,000 hours in a QUV weatherometer, ASTM G 53</b>				
ASTM C 1135	Tensile Adhesion Strength	at 25% extension	psi (MPa)	35 (0.241)
		at 50% extension	psi (MPa)	50 (0.345)

<sup>1</sup>Based on South Coast Air Quality Management District of California. Maximum VOC is listed both inclusive and exclusive of water and exempt compounds. For a VOC data sheet for a specific sealant color, please send your request to [product.inquiry@dowcorning.com](mailto:product.inquiry@dowcorning.com).

### DESCRIPTION

*Dow Corning*® 795 Silicone Building Sealant is a one-part, neutral-cure, architectural-grade sealant that easily extrudes in any weather and cures quickly at room temperature.

This cold-applied, non-sagging silicone material cures to a medium-modulus silicone rubber upon exposure to atmospheric moisture. The cured sealant is durable and flexible enough to accommodate ±50 percent movement of original joint dimension when installed

in a properly designed weatherseal joint. In a properly designed structurally glazed joint, the sealant is strong enough to support glass and other panel materials under high windload.

### APPROVALS/ SPECIFICATIONS

*Dow Corning* 795 Silicone Building Sealant meets the requirements of:

- Federal Specification TT-S-001543A (COM-NBS) Class A for silicone building sealants
- Federal Specification TT-S-00230C

<sup>1</sup>*Kynar* is a trademark of Atofina Chemicals Inc.

<sup>2</sup>Contact your local Dow Corning Sales Application Engineer for specifics.

(COM-NBS) Class A for one-component building sealants

- ASTM Specification C 920 Type S, Grade NS, Class 50, Use NT, G, A and O
- ASTM Specification C 1184 for structural silicone sealants
- Canadian Specification CAN2-19.13-M82

## COLORS

*Dow Corning 795 Silicone Building Sealant* is available in 11 colors: black, white, gray, limestone, bronze, sandstone, adobe tan, dusty rose, rustic brick, blue spruce and charcoal. Custom colors may be ordered to match virtually any substrate.

## HOW TO USE

Please consult the *Dow Corning Americas Technical Manual*, Form No. 62-1112, for detailed information on state-of-the-art application methods and joint design. Please contact your local Dow Corning Sales Application Engineer for specific advice.

## Preparation

Clean all joints, removing all foreign matter and contaminants such as grease, oil, dust, water, frost, surface dirt, old sealants or glazing compounds and protective coatings.

## Application Method

Install backing material or joint filler, setting blocks, spacer shims and tapes. Mask areas adjacent to joints to ensure neat sealant lines. Primer is generally not required on non-porous surfaces, but may be necessary for optimal sealing of certain porous surfaces. A test placement is always recommended. Apply *Dow Corning 795 Silicone Building Sealant* in a continuous operation using positive pressure. (The sealant can be applied using many types of air-operated guns and most types of bulk dispensing equipment.) Before a skin forms (typically within 15 minutes), tool the sealant with light pressure to spread the sealant against the backing material and

joint surfaces. Remove masking tape as soon as the bead is tooled.

## HANDLING PRECAUTIONS

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND MATERIAL SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE MATERIAL SAFETY DATA SHEET IS AVAILABLE ON THE DOW CORNING WEBSITE AT WWW.DOWCORNING.COM, OR FROM YOUR DOW CORNING SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CORNING CUSTOMER SERVICE.

## USABLE LIFE AND STORAGE

When stored at or below 27°C (80°F), *Dow Corning 795 Silicone Building Sealant* has a shelf life of 12 months from the date of manufacture. Refer to product packaging for "Use By Date."

## PACKAGING

*Dow Corning 795 Silicone Building Sealant* is supplied in 10.3-fl oz (305-mL) disposable plastic cartridges that fit ordinary caulking guns, 20-fl oz (590-mL) sausages and 2- and 4.5-gal (7.5- and 17-L) bulk containers.

## LIMITATIONS

*Dow Corning 795 Silicone Building Sealant* should not be used:

- In structural applications without prior review and approval by your local Dow Corning Sales Application Engineer
- In below-grade applications
- When surface temperatures exceed 50°C (122°F) during installation
- On surfaces that are continuously immersed in water
- On building materials that bleed oils, plasticizers or solvents that may affect adhesion
- On frost-laden or wet surfaces
- In totally confined joints (the sealant requires atmospheric moisture for cure)
- If the sealant is intended to be painted (paints do not typically adhere to most silicone sealants)
- To surfaces in direct contact with food or other food-grade applications

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

## HEALTH AND ENVIRONMENTAL INFORMATION

To support customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

For further information, please see our website, [www.dowcorning.com](http://www.dowcorning.com), or consult your local Dow Corning Sales Application Engineer.

## LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that Dow Corning's products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that the product will meet the Dow Corning sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

## DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

## DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

A 20-year Weatherseal Limited Warranty is available. Some testing may be required. Consult your Dow Corning Sales Application Engineer for details.

